


PLACCEL 410

Polycaprolactone tetraol

<Description>

PLACCEL 410 is polycaprolactone tetraol which has four primary hydroxyl groups and its molecular weight is 1030. It can be used as a urethane resin cross-linking agent and raw material of the coating. At the same time as it can form advanced bridge structure, the flexibility which is the feature which polycaprolactone has can be demonstrated.



<Composition / Information on ingredients>

Composition of Polycaprolactone Tetraol (PLACCEL 410)

Chemical Name of Component	Composition of the Sample	Unit (%)
Polycaprolactone tetraol	100%	1000000

Global Regulation

RoHS	REACH	SVHC	Phthalates	PAHs	PCBs	PBBs	PFOS	PFOs	Perfluorinated	Phthalates
✓	✓	✓	✓	✓	✓	✓				✓

(*) Some restrictions applied to products

Typical properties

Temp.	Mn	Mw/Mn	Inherent Viscosity (dl/g)	Density (g/cm ³)		Specific Gravity (20/20)		Flash Point (°C)	Boiling Point (°C)
				20°C	25°C	20°C	25°C		
25	1030	1.48	0.15	0.91	0.91	0.91	170	270	

It should be noted that typical property values shown in this technical data sheet are representative values and are not guaranteed values. Please contact us to obtain detail of product and guaranteed values.

Please refer to our SDS (safety data sheet) for information on the handling of each product.

DAICEL CORPORATION

Chemical Division, Industrial Chemicals
Organic Chemical Marketing Group
4-1-1, Honjo, Bunkyo-ku,
Tokyo, 113-8501, Japan

TEL: 03-3271-8111
FAX: 03-3271-8119
E-MAIL: daicel@daicel.com